

FORM PTO-1500 (Mod/Fied)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES  
DESIGNATED/ELECTED OFFICE (DO/EO/US)  
CONCERNING A FILING UNDER 35 U.S.C. 371

RDID0041US

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/555618

INTERNATIONAL APPLICATION NO.

PCT/EP98/07851

INTERNATIONAL FILING DATE

3 December 1998

PRIORITY DATE CLAIMED

4 December 1997

TITLE OF INVENTION

MODIFICATION OF SURFACES TO INCREASE THE SURFACE TENSION

APPLICANT(S) FOR DO/EO/US

Volker ZIMMER and Hans-Peter BRAUN


Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
  - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ has been transmitted by the International Bureau.
  - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
  - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ have been transmitted by the International Bureau.
  - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
  - d. ☐ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)). **(unexecuted)**
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

## Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☒ Certificate of Mailing by Express Mail
20. ☒ Other items or information:

Certified Copy of Priority German Application Serial No. 197 53 848.7;  
General Appointment of Representative for U.S. Patent and Patent Application; and  
Return postcard.

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.53) <b>09/555618</b>		INTERNATIONAL APPLICATION NO. <b>PCT/EP98/07851</b>		ATTORNEY'S DOCKET NUMBER <b>RDID0041US</b>			
21. The following fees are submitted: <b>BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :</b> <input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO . . . . . \$970.00 <input checked="" type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO . . . . . \$840.00 <input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO . . . . . \$690.00 <input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) . . . . . \$670.00 <input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) . . . . . \$96.00  <b>ENTER APPROPRIATE BASIC FEE AMOUNT =</b>				<b>CALCULATIONS PTO USE ONLY</b>  <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;"><b>\$840.00</b></td> <td style="width: 50%;"></td> </tr> </table>		<b>\$840.00</b>	
<b>\$840.00</b>							
Surcharge of <b>\$130.00</b> for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).				<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;"></td> <td style="width: 50%; text-align: center;"><b>\$0.00</b></td> </tr> </table>			<b>\$0.00</b>
	<b>\$0.00</b>						
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE				
Total claims	- 20 =	0	x \$18.00	<b>\$0.00</b>			
Independent claims	- 3 =	0	x \$78.00	<b>\$0.00</b>			
Multiple Dependent Claims (check if applicable) <input type="checkbox"/>				<b>\$0.00</b>			
<b>TOTAL OF ABOVE CALCULATIONS =</b>				<b>\$840.00</b>			
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable). <input type="checkbox"/>				<b>\$0.00</b>			
<b>SUBTOTAL =</b>				<b>\$840.00</b>			
Processing fee of <b>\$130.00</b> for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).				<b>\$0.00</b>			
<b>TOTAL NATIONAL FEE =</b>				<b>\$840.00</b>			
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). <input type="checkbox"/>				<b>\$0.00</b>			
<b>TOTAL FEES ENCLOSED =</b>				<b>\$840.00</b>			
				Amount to be refunded	\$		
				charged	\$		
<input type="checkbox"/> A check in the amount of _____ to cover the above fees is enclosed.							
<input checked="" type="checkbox"/> Please charge my Deposit Account No. <b>50-0877</b> in the amount of <b>\$840.00</b> to cover the above fees. A duplicate copy of this sheet is enclosed.							
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. <b>50-0877</b> . A duplicate copy of this sheet is enclosed.							
<b>NOTE:</b> Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.							
SEND ALL CORRESPONDENCE TO							
Richard T. Knauer Roche Diagnostics Corporation 9115 Hague Road, Bldg. D P.O. Box 50457 Indianapolis, IN 46250-0457 Telephone No.: (317) 576-7464 Facsimile No.: (317) 576-2883							
 SIGNATURE							
<b>Richard T. Knauer</b> NAME							
<b>35,575</b> REGISTRATION NUMBER							
<b>1 June 2000</b> DATE							

Docket No. RDID 0041US

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: Zimmer et al.

Application No.: 09/555,618

Group No.: Unknown

Filed: 01 June 2000

Examiner: Unknown

For: MODIFICATION OF SURFACES TO INCREASE THE SURFACE TENSION

Assistant Commissioner for Patents  
Washington, D.C. 20231

PRELIMINARY AMENDMENT

Sir:

Entry of the following amendments prior to examination of the above-referenced application is respectfully requested.

In the specification

At page 1 line 1, please add --Background and Summary of the Invention--.

At page 5 line 5, please add --Detailed Description of the Invention--.

In the claims

Please amend claims 1, 5, 8, 9, 12, 13, and 15 as follows:

1. (Amended) Process for the production of a surface coating to increase surface tension of objects, ~~comprising depositing~~ [wherein] a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water [is deposited] on an object and this is at least superficially oxidized by the subsequent action of boiling water or water [vapour] ~~vapor~~ on the deposited layer.

5. (Amended) Use of a surface coating as claimed in claim 3 [or 4], wherein the element is derived from the following group of elements: Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.

8. (Amended) Use of a surface coating as claimed in [claims 3 or 4] ~~claim 3~~, wherein the alloy contains at least two components from the following group of elements: Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.

9. Use of a surface coating as claimed in claim 3 [or 4], wherein the alloy contains at least one component from the following first group of elements: Al, Si, Ti, V, Cr.

Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb, which are alloyed with at least one element from the following second group of elements: Mg, Ca, Sr, Ba.

12. (Amended) Use of a surface coating as claimed in [one of the claims 3 to 11] claim 3, wherein the deposited layer has a thickness between 1 nm and 500 nm.

13. (Amended) Use of a surface coating as claimed in [one of the claims 3 to 11] claim 3, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

15. (Amended) Analytical test element in which the sample liquid is transported from a sample application site to a determination site, where a detection site lies upstream of the sample application site in the transport direction, wherein the analytical test element [has] comprises at least one surface which is composed of at least one element that can be oxidized with water or an alloy that can be oxidized with water which has been treated by the action of boiling water or water [vapour] vapor.

Please add new claims 16-28 as follows:

16. Use of a surface coating as claimed in claim 4, wherein the element is derived from the following group of elements: Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.

17. Use of a surface coating as claimed in claim 4, wherein the alloy contains at least two components from the following group of elements: Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.

18. Use of a surface coating as claimed in claim 4, wherein the alloy contains at least one component from the following first group of elements: Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb, which are alloyed with at least one element from the following second group of elements: Mg, Ca, Sr, Ba.

19. Use of a surface coating as claimed in claim 4, wherein the deposited layer has a thickness between 1 nm and 500 nm.

20. Use of a surface coating as claimed in claim 4, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

21. Use of a surface coating as claimed in claim 5, wherein the deposited layer has a thickness between 1 nm and 500 nm.

22. Use of a surface coating as claimed in claim 5, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

23. Use of a surface coating as claimed in claim 8, wherein the deposited layer has

a thickness between 1 nm and 500 nm.

24. Use of a surface coating as claimed in claim 8, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

25. Use of a surface coating as claimed in claim 9, wherein the deposited layer has a thickness between 1 nm and 500 nm.

26. Use of a surface coating as claimed in claim 9, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

27. Process of claim 1 wherein the deposited layer has a thickness between 1 nm and 500 nm.

28. Process of claim 1 wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.

#### REMARKS


The specification has been amended at page 1 line 1 and page 5 line 5 to add headings to the application. No new matter is believed to be added by virtue of the amendments to the specification.

Claims 1 and 15 have been amended to correct a typographical error and to include the transitional phrase "comprising". Claims 5, 8, 9, 12, and 13 have been amended to remove their multiple dependencies. Claims 16-28 have been added to point out more specifically the subject matter of the present invention. Support for the new claims is found throughout the specification. No new matter is added by virtue of the amendments to the claims or of the new claims.

The claims as submitted herein are believed to be in condition for allowance, and allowance of the application is respectfully requested. It is requested that this paper be considered a Petition for Extension of time sufficient to effect a timely response, and that all fees due be charged to Deposit Account Number 50-0877 with reference to (RDID 0041 US).

Respectfully submitted,

Date: January 5, 2001

  
Jill L. Woodburn, Reg. 39,874

The Law Office of Jill L. Woodburn, L.L.C.  
6633 Old Stonehouse Dr.  
Newburgh, IN 47630  
Telephone No. (812) 842-2218  
Facsimile No. (812) 842-2660

09/555618

426 Recd POT/200

01 JUN 2000

Boehringer Mannheim GmbH

4628/00/

### **Modification of surfaces to increase the surface tension**

The invention concerns a process for the production of surface coatings as well as the use of a surface coating to increase the surface tension of objects.

The coating of surfaces of solid objects is a widely used means of specifically changing the surface properties of objects. Here reference is only made to the countless methods of corrosion protection for everyday objects made of base metals or the painting of objects with the aim of changing their optical appearance.

Coating is usually understood as a manufacturing process for applying a firmly adhering layer of a shapeless material to a work piece or a supporting sheet. One can in principle distinguish between four groups of coating processes which each differ by the state of the coating material before coating:

1. Coating from a gaseous or vaporous state such as evaporation coating or metallizing;
2. Coating from a liquid, pulpy or paste-like state such as painting, dispersion or hot-melt coating;
3. Coating from an ionized state by electrolytic or chemical depositing such as among others the eloxal process or electrophoretic painting.
4. Coating from a solid i.e. granular or powder state such as powder coating or coating by

sintering.

Plastics have turned out to be the production material of choice for fields of application in which cheap single-use articles are used especially in medical diagnostics or environmental analysis. Since plastics and in particular cheap, easy-to-process commodity plastics that can be almost shaped at will, are usually composed of non-polar organic polymers, most of them cannot be wetted or only poorly wetted by polar media such as water and aqueous liquids, in particular biological samples. This property is utilized for certain applications especially where adherence of the liquid to the plastic object is not desired such as for disposable pipette tips. On the other hand there are numerous fields of applications for plastic objects in which a wettability with polar liquids is desired such as for example in the field of rapid diagnostics in which plastics can serve as materials for taking up biological sample liquids.

There is therefore no lack of different processes which have the aim of hydrophilically modifying plastic surfaces. Hydrophilic surfaces are characterized by a high surface tension which have a value near to the value of the surface tension of water (72 mN/m). Examples of a hydrophilic modification of plastic surfaces are corona plasma treatment, plasma chemical vapour deposition (PACVD, e.g. Antec Co. Kelkheim), the covalent binding of hydrophilic polymers with a photoreactive capability onto a plastic surface described for example in US 4,973,493 (Photo Link Surface, BSI Corporation Co., Eden Prairie, Minnesota, USA), the application of layers containing wetting agents onto a plastic surface (for example Adhesive

Research Co., Glen Rock, PA, USA) or coating of inorganic-organic nanocomposites by means of sol-gel technology on the surfaces to be modified (for example INM, Co. Saarbrücken).

The processes mentioned above which each have advantages and disadvantages have been able to establish themselves for the hydrophilic modification of plastic surfaces whether of foils or formed pieces.

The corona plasma treatment leads to an increase in the surface tension which continuously decreases after the treatment over a short period of several days up to a few weeks. Moreover the surface tensions that can be achieved are relatively low.

Slightly higher surface tensions than those of the corona plasma treatment can be achieved with the PACVD technology. Although this method leads to surface coatings that are more stable over time, a decrease of the surface tension with time is still observed in this case.

Surfaces which are furnished with so-called photo link surfaces or which have been coated with layers containing wetting agents have a surface tension which is stable over time. However, both variants do not lead to optimally high surface tensions. An additional fundamental disadvantage of coating with layers containing wetting agents is that the wetting agents accumulate in a liquid aqueous sample that is contacted with the layer and can thus change it or make it unusable.



Coating of inorganic-organic nanocomposites by means of sol-gel technology on the surfaces to be modified leads to increased surface tensions. However, a disadvantage is that the process itself is very complicated and time-consuming which is why it does not appear to be suitable for modifying mass-produced plastic articles.

The object of the present invention was to eliminate the disadvantages of the prior art. In particular it was intended to provide surface coatings with a high surface tension that are stable over time to be used for example for the hydrophilic modification of objects. Moreover it should be possible to carry out the coating in a simple and reliable manner in order to be suitable for the modification of mass-produced articles.

The object is achieved by the subject matter of the invention as characterized in the patent claims.

The invention concerns a process for the production of a surface coating to increase the surface tension of objects characterized in that a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water is deposited on an object and this is at least superficially oxidized by the subsequent action of boiling water or water vapour on the deposited layer.

The invention additionally concerns the use of a surface coating to increase the surface tension of objects characterized in that the surface coating is obtained by deposition of a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water and subsequent action of boiling water or

water vapour on the deposited layer.

Boiling water or water vapour and particularly preferably deionized water is preferably used to treat the deposited surface coating.

The increase in the surface tension results from an increase in the polarity and corresponds to an increased hydrophilicity of the observed surfaces. The hydrophilicity is the water affinity of a surface. In this connection hydrophilic surfaces are water-attracting surfaces. Aqueous samples also including biological samples like blood, urine, saliva, sweat and samples derived therefrom such as plasma and serum spread well on such surfaces. Such surfaces are characterized among others in that a boundary surface of a water drop forms an acute rim or contact angle on them (cf. for example the statements under the entry "Benetzung" in the "CD Römpf Chemie Lexikon" version 1.0, 1995). In contrast an obtuse rim angle is formed at the interface between a water drop and a surface on hydrophobic i.e. water repellent surfaces.

The rim angle which is a result of the surface tensions of the test liquid and of the surface to be examined is a measure of the hydrophilicity of a surface. Water for example has a surface tension of 72 mN/m. If the value of the surface tension of the observed surface is much below this value i.e. more than 20 mN/m, then the wetting is poor and the resulting rim angle is obtuse. Such a surface is referred to as hydrophobic. If the surface tension approximates the value which is found for water then the wetting is good and the rim angle is acute. If, in contrast, the surface tension is the same

as or higher than that of the value found for water, then the drop runs and there is a total spreading of the liquid. It is then no longer possible to measure a rim angle. Surfaces which form an acute rim angle with water drops or on which a total spreading of a water drop is observed are referred to as hydrophilic.

According to the invention the surface coating should be carried out by depositing a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water on an object. All objects come into consideration as objects to be coated whose surface in the uncoated state has a lower hydrophilicity than in the coated state after treatment. Examples are plastic, metal, glass, ceramics, paper, fleece, cardboard etc. where the objects can have any shape e.g. flat, three-dimensional or porous.

All 4 coating processes mentioned above can in principle be used to deposit the layer i.e. coating from a gaseous or vaporous state, from a liquid, pulp or paste-like state, from an ionized state or from a solid state. The coating is preferably carried out from a gaseous state. A layer of an element or an alloy that can be oxidized with water is particularly preferably applied to the surface to be modified in a vacuum coater. This process is for example used cost-effectively for large surfaces for the packaging industry and electrical industry for example with aluminium as the element that can be oxidized with water.

The layers can be applied to the object to be coated as a continuous layer covering the whole area but also in the form of any two-dimensional patterns.

It is essential for the subject matter of the invention that the deposited layer of the element that can be oxidized with water or alloy that can be oxidized with water is subsequently treated by the action of boiling water or water vapour after the actual coating process. In this case it is sufficient to allow boiling water or water vapour to act at normal pressure. However, it is preferably to use superheated water vapour since this considerably reduces the exposure times. For example a 30 nm thick aluminium layer can be completely oxidized through with superheated water vapour within ca. 45 s.

In this treatment the deposited layer of the element that can be oxidized with water or the alloy that can be oxidized with water is at least superficially oxidized. In this process at least the surface of the deposited layer of the element that can be oxidized with water or the alloy that can be oxidized with water loses its elemental properties. In the case of metals or alloys thereof this means among others the loss of lustre and conductivity. In this process the oxidation of the surface goes beyond the layer that may be present as a natural protective layer. Thin metallic layers are oxidized during treatment with boiling water or water vapour to such an extent that they completely lose their metallic appearance and may become completely transparent.

The treatment with boiling water or water vapour is preferably carried out with pure water and preferably with deionized water (for example aqua purificata according to DAB). The surfaces obtained in this process are not contaminated with chemicals which are found in other oxidation processes in particular wet chemical oxidation processes such as oxidation with oxidizing

acids. Purification and rinsing steps can therefore be omitted and make the process more simple and cost-effective.

According to the invention it is possible to use base elements for the coating which can be oxidized by boiling water or water vapour. The elements Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb are preferred. Al, Si, Ti, Zr are particularly preferred. Al is quite especially preferred.

Base alloys that can be oxidized by boiling water or water vapour can also be used according to the invention. These are preferably alloys which contain at least two components from the following group of elements comprising Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn and Sb. An alloy of 99 % by weight Al and 1 % by weight Si is for example suitable.

Alloys are also suitable which contain at least one component from the following first group of elements comprising Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn and Sb which are alloyed with at least one element from the following second group of elements comprising Mg, Ca, Sr and Ba such as for example an alloy of 95 % by weight Al and 5 % by weight Mg. Alloys are particularly preferred which contain at least one component from the following first group of elements comprising Al, Si, Ti and Zr which are alloyed with at least one element of the following second group of elements comprising Mg, Ca, Sr and Ba. Alloys that are composed of aluminium which is alloyed with at least one element from the following group of elements

comprising Mg, Ca, Sr and Ba are quite especially preferred.

The deposited coat according to the invention preferably has a thickness of 1 nm to 500 nm. The action of boiling water or water vapour on the deposited layer leads to the formation of oxide layers which are preferably between 0.1 nm and 500 nm, particularly preferably between 10 nm and 100 nm thick.

The surface coatings produced according to the invention are homogeneous inorganic oxide layers which have a high surface tension and high polarity, which are stable over a long period and have a good adherence with concomitant elasticity on the coated object.

The characterization of surfaces with high surface tensions (high-energy surfaces) causes certain technical measurement problems. In various measuring methods such as contact angle measurement the interfacial effects of the surface to be examined relative to test liquids are used. Since it is hardly possible to produce test liquids with surface tensions that are considerably above the value for water (72 mN/m), there are certain limits to being able to extrapolate above this value. Kinetic effects also add to the problems. A liquid which wets a surface, spreads over a short period typically less than 1.5 s. However, spontaneous wetting is important for the determination of the surface tension with regard to capillary activity. In dynamic contact angle methods one refers to the progressive angle of wetting of a drop that is becoming continuously larger. However, the dosing of the drop and measurement of the drop with commercially available automated contact angle

measuring instruments is too slow for the hydrophilic surface coatings presented here to be able to unequivocally describe the surface coatings according to the invention. It therefore turned out to be practical to measure the surface coating according to the invention by comparative determination of the filling time of a test capillary.

The cylindrical test capillary is composed of two parallel opposing foils which are kept at a defined distance from one another by an exactly defined spacer in the form of a double-sided adhesive tape which determines the length, width and height dimensions of the capillary. The opposing surfaces of the two foils are provided with the coating to be tested. The dimensions of the capillary are 0.1 mm height, 2 mm width and 15 mm length where the length of the capillary corresponds to the available transport path of the liquid and the height of the capillary is that dimension which causes the capillarity. The capillary has an opening that serves to take up the test liquid with a cross-sectional area of 0.1 mm x 2 mm which corresponds to the base area of the cylindrical capillary. A vent opening is provided at the opposite end of the capillary which allows the displaced air in the capillary to escape when the test liquid is sucked in. The test liquid is preferably distilled water or aqua purificata according to DAB but it is also possible to use other test liquids depending on the field of application of the surface coating such as blood or other body fluids. The filling times for the test liquids are measured at half (7.5 mm transport path) and complete filling (15 mm transport path). Comparative results are described in example 1.

The surface coatings are particularly preferably used according to the invention in analytical test elements to increase the hydrophilicity. The invention therefore also concerns an analytical test element or a test strip in which the sample liquid is transported from a sample application site to a determination site in which a detection site lies upstream of the sample application site in the transport direction. In this connection it is important that the analytical test element has at least one surface which is composed of at least one element that can be oxidized with water or an alloy that can be oxidized with water which has been treated by the action of boiling water or water vapour. The materials described above come into consideration as elements and alloys.

Surfaces that have been made hydrophilic are especially essential for capillary gap test elements. Capillary gap test elements are test elements in which the sample liquid is moved in a transport channel (capillary channel, capillary gap) from a sample application site to a distant sample detection site with the aid of capillary forces in order to undergo a detection reaction at this site.

The ability of a capillary to suck up a liquid depends on the wettability of the channel surface with the liquid. This means for aqueous samples that a capillary should be manufactured from a material whose surface tension almost reaches 72 mN/m or exceeds this value.

Sufficiently hydrophilic materials for the construction of a capillary which rapidly sucks up aqueous samples are for example glass, metal or ceramics. However, these



materials are unsuitable for use in test carriers since they have some disadvantages such as risk of breaking in the case of glass or ceramics. Therefore plastic foils or moulded parts are usually used to manufacture test elements. As a rule the plastics used hardly exceed a surface tension of 45 mN/m. Even with the, in a relative sense, most hydrophilic plastics such as polymethylmethacrylate (PMMA) or polyamide (PA) it is only possible - if at all - to construct slowly sucking capillaries. Capillaries made of hydrophobic plastics such as for example polystyrene (PS), polypropylene (PP) or polyethylene (PE) essentially do not suck aqueous samples. Consequently it is necessary to endow the plastics used as a construction material for test elements with capillary active channels with hydrophilic properties i.e. to hydrophilize them.

Therefore in analytical test elements with capillary gaps at least one, but preferably two and especially preferably two opposing surfaces which form the inner surface of the channel capable of capillary liquid transport are preferably hydrophilized. If more than one surface is hydrophilized then the surfaces can either be made hydrophilic using the same or different methods. Hydrophilization is particularly necessary when the materials that form the capillary active channel are themselves hydrophobic or only very slightly hydrophilic because they are for example composed of nonpolar plastics. Nonpolar plastics such as for example polystyrene (PS), polyethylene (PE), polyethylene terephthalate (PET) or polyvinyl chloride (PVC) are advantageous as carrier materials because they do not absorb the liquids to be examined and thus the sample volume can be effectively utilized by the detection reaction. The hydrophilization of the surface of the

capillary channel enables a polar, preferably aqueous, sample liquid to readily enter the capillary channel and be rapidly transported there to the site of the test element where the detection takes place.

The hydrophilization is quite especially preferably achieved by using thin layers of oxidized aluminium. These layers are either applied directly to the desired components of the test element for example by vacuum coating the work pieces with metallic aluminium and subsequently oxidizing the metal, or by using metal foils or metal-coated plastics for the construction of the test carriers which also have to be oxidized to achieve the desired hydrophilicity. In this case metal layer thicknesses of 1 to 500 nm are adequate. The metal layer is subsequently oxidized to form the oxidized form whereby according to the invention oxidation in the presence of water vapour or by boiling in water have proven to be especially suitable methods. The oxide layers formed in this manner are between 0.1 and 500 nm, preferably between 10 and 100 nm thick depending on the method. Larger layer thicknesses of the metal layer as well as of the oxide layer can in principle be realised in practice but do not exhibit any additional advantageous effects.

Further applications according to the invention of surface coatings are

- making polymer foils, fabrics, fleeces or three-dimensional formed pieces hydrophilic and detergent-free to improve their adhesive properties for paint, adhesive or plastic coats,

- adsorptive binding of polar molecules or materials in particular for the adsorption of biologically active molecules such as proteins, enzymes, antibodies, nucleic acids (cf for example Chem. Pharm. Bull. **41**, (1993) 1055) since the increased surface tension is associated with an increase in the polarity of the surface,
- production of surface patterns such as cross-pieces for the transport of polar liquids, for a defined boundary between polar and nonpolar areas in which case these patterns can be produced by the structure of the deposited material itself or subsequently by selectively covering certain areas of the deposited material layer with for example wax when it is treated with boiling water or water vapour.

The invention is elucidated by the following example.

#### Example 1

Comparison of the filling times of a test capillary

A cylindrical test capillary was constructed from two parallel opposing foils which are kept at a defined distance from one another by an exactly defined spacer in the form of a double-sided adhesive tape which determines the length, width and height dimensions of the capillary. The opposing surfaces of the two foils were provided with the coating to be tested. The foils that were used were polyester foils (Melinex<sup>®</sup>, ICI)

which were variously modified as follows.

- 1.) Foil which was coated with photoreactively equipped hydrophilic polymers (BSI)
- 2.) Foil which was subjected to a corona plasma treatment (Antec)
- 3.) Foil on which a layer containing a wetting agent was applied (A.R.)
- 4.) Foil on which inorganic-organic nanocomposites were coated by means of sol-gel technology (INM)
- 5.) Foil on which aluminium oxide was vapour deposited but which was not subsequently treated with boiling water or water vapour (Alu-Ox).
- 6.) Foil on which firstly a layer of aluminium of 30 nm thickness was vapour deposited which was subsequently completely oxidized for 45 s with water vapour (Alu-Ox/H<sub>2</sub>O).

The dimensions of the capillary are 0.1 mm height, 2 mm width and 15 mm length where the length corresponds to the transport path of the liquid and the height is that dimension which causes the capillarity. The capillary has an opening that serves to take up the test liquid with a cross-sectional area of 0.1 mm x 2 mm which corresponds to the base area of the cylindrical capillary. A vent opening is provided at the opposite

end of the capillary which allows the displaced air in the capillary to escape when the test liquid is sucked in. The test liquid was in one case distilled water, aqua purificata according to DAB and in the other case human blood (containing EDTA as an anticoagulant, haematocrit 44 %). The filling times for the test liquids were measured at half (7.5 mm transport path) and complete filling (15 mm transport path). The capillary was kept vertical during filling so that the test liquid had to cover the filling path of 15 mm against the force of gravity. The comparative results are shown in Table 1.

TABLE 1

Coating	Filling time for blood [s]		Filling time for water [s] after 15 mm
	after 7.5 mm	after 15 mm	
BSI	0.5-0.6	2.1-2.7	0.6-0.9
Antec	1.4-2.3	4.7-8.4	4.0-7.0
A.R.	0.4-0.5	1.8-2.1	0.4-0.5
INM		1.0-3.0	
Alu-Ox	-	1.2	-
Alu-Ox/H <sub>2</sub> O	0.2-0.3	0.7	< 0.2

The coating according to the invention (Alu-Ox/H<sub>2</sub>O) is the one which wets most actively among all tested layers. The coating according to the invention (Alu-Ox/H<sub>2</sub>O) produced by the action of water vapour after coating the metal has a considerably improved

hydrophilicity compared to a surface (Alu-Ox) that was coated directly with aluminium oxide but was not oxidized by the action of water vapour. The production process according to the invention is relatively simple, can be controlled well and leads to stable coatings with high surface tensions that remain constant over time.

### Claims

1. Process for the production of a surface coating to increase surface tension of objects, wherein a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water is deposited on an object and this is at least superficially oxidized by the subsequent action of boiling water or water vapour on the deposited layer.
2. Process as claimed in claim 1, wherein the surface coating is obtained by deposition of a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water and subsequent action of superheated water vapour.
3. Use of a surface coating to increase the surface tension of objects, wherein the surface coating is obtained by deposition of a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water and subsequent action of boiling water or water vapour on the deposited layer.
4. Use of a surface coating as claimed in claim 3, wherein the surface coating is obtained by deposition of a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water and subsequent action of superheated water vapour.

5. Use of a surface coating as claimed in claim 3 or 4, wherein the element is derived from the following group of elements:  
Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.
6. Use of a surface coating as claimed in claim 5, wherein the element is derived from the following group of elements:  
Al, Si, Ti, Zr.
7. Use of a surface coating as claimed in claim 6, wherein the element is Al.
8. Use of a surface coating as claimed in claims 3 or 4, wherein the alloy contains at least two components from the following group of elements:  
Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb.
9. Use of a surface coating as claimed in claim 3 or 4, wherein the alloy contains at least one component from the following first group of elements:  
Al, Si, Ti, V, Cr, Mn, Fe, Co, Ni, Zn, Ga, Ge, Zr, Nb, Cd, In, Sn, Sb,  
which are alloyed with at least one element from the following second group of elements:  
Mg, Ca, Sr, Ba.
10. Use of a surface coating as claimed in claim 9, wherein the alloy contains at least one component from the following first group of elements:  
Al, Si, Ti, Zr,



which is alloyed with at least one element from the following second group of elements:

Mg, Ca, Sr, Ba.

11. Use of a surface coating as claimed in claim 10, wherein the alloy is composed of Al which is alloyed with at least one element from the following group of elements:  
Mg, Ca, Sr, Ba.
12. Use of a surface coating as claimed in one of the claims 3 to 11, wherein the deposited layer has a thickness between 1 nm and 500 nm.
13. Use of a surface coating as claimed in one of the claims 3 to 11, wherein the superficial oxide layer has a thickness between 0.1 nm and 500 nm.
14. Use of a surface coating as claimed in claim 13, wherein the superficial oxide layer has a thickness between 10 nm and 100 nm.
15. Analytical test element in which the sample liquid is transported from a sample application site to a determination site, where a detection site lies upstream of the sample application site in the transport direction, wherein the analytical test element has at least one surface which is composed of at least one element that can be oxidized with water or an alloy that can be oxidized with water which has been treated by the action of boiling water or water vapour.

### **Abstract**

The invention concerns a process for the production of a surface coating as well as the use of surface coatings to increase the surface tension of objects, which is characterized in that the surface coating is obtained by depositing a layer of at least one element that can be oxidized with water or an alloy that can be oxidized with water and subsequent action of boiling water or water vapour on the deposited layer.

Docket No.  
RDID0041US

# Declaration and Power of Attorney For Patent Application

## English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

### MODIFICATION OF SURFACES TO INCREASE THE SURFACE TENSION

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on June 1, 2000 as United States Application No. or PCT International Application Number 09/555,618 and was amended on \_\_\_\_\_ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Not Claimed

PCT/EP98/07851

(Number)  
197 53 848.7

(Number)

(Number)

PCT

(Country)  
Germany

(Country)

(Country)

3 December 1998

(Day/Month/Year Filed)  
4 December 1997

(Day/Month/Year Filed)

(Day/Month/Year Filed)

☐

☐

☐

I hereby claim the benefit under 35 U.S.C. Section 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)

(Filing Date)

(Application Serial No.)

(Filing Date)

(Application Serial No.)

(Filing Date)

I hereby claim the benefit under 35 U. S. C. Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. Section 112, I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, C. F. R., Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Application Serial No.)

(Filing Date)

(Status)  
(patented, pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status)  
(patented, pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status)  
(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)

Richard T. Knauer, Reg. No. 35,575

D. Michael Young, Reg. No. 33,819

Brent A. Harris, Reg. No. 39,215

Kenneth J. Waite, Reg. No. 45,189

Marilyn L. Amick, Reg. No. 30,444

Jill Lynn Woodburn, Reg. No. 39,874

(6)

Send Correspondence to: Richard T. Knauer  
Roche Diagnostics Corporation  
9115 Hague Road, Bldg. D, P.O. Box 50457  
Indianapolis, IN 46250-0457

Direct Telephone Calls to: (name and telephone number)

Richard T. Knauer, Telephone No. (317) 576-7464

Full name of sole or first inventor

**ZIMMER, Volker**

Sole or first inventor's signature

*Volker Zimmer*

Date

✓ 25.10.2000

Residence

**Wilhelmstrasse 64, D-69221 Dossenheim, Germany**

*DEX*

Citizenship

**German**

Post Office Address

(same as residence)

Full name of second inventor, if any

**BRAUN, Hans-Peter**

Second inventor's signature

*Hans Peter Braun*

Date

✓ 28.10.2000

Residence

**Wintergasse 25, D-69469 Weinheim, Germany**

*DEX*

Citizenship

**German**

Post Office Address

(same as residence)

Please type a plus sign (+) inside this box → ☒

PTO/SB/122 (11-96)

Approved for use through 6/30/99. OMB 0651-0035

Patent and Trademark Office. U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

<b>CHANGE OF CORRESPONDENCE ADDRESS</b> <i>Application</i>  Address to: Assistant Commissioner for Patents Washington, D.C. 20231	Application Number	09/555,618
	Filing Date	01 June 2000
	First Named Inventor	ZIMMER et al.
	Group Art Unit	
	Examiner Name	
	Attorney Docket Number	RDID 0041 US

Please change the Correspondence Address for the above-identified application to:

☐

Customer Number

Type Customer Number here

Place Customer  
Number Bar Code  
Label here

OR

☒ Firm or  
Individual Name

The Law Office of Jill L. Woodburn, J.L.C.

Address

Attn: Jill L. Woodburn

Address

6633 Old Stonehouse Dr.

City

Newburgh

State

IN

ZIP

47630

Country

US

Telephone

(812) 842-2660

Fax

(812) 842-2660

This form cannot be used to change the data associated with a Customer Number. To change the data associated with an existing Customer Number use "Request for Customer Number Data Change" (PTO/SB/124).

I am the :

☐

Applicant.

☐

Assignee of record of the entire interest.  
Certificate under 37 CFR 3.73(b) is enclosed.

☒

Attorney or agent of record.

Typed or  
Printed Name

Jill L. Woodburn Reg. 39,874

Signature

Date

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington DC 20231.

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Assistant Commissioner for Patents  
Washington, DC 20231


**GENERAL APPOINTMENT OF REPRESENTATIVE FOR**  
**U.S. PATENT AND PATENT APPLICATION**

(5)  
The undersigned applicant or assignee hereby appoints D. Michael Young, Reg. No. 33,819, Richard T. Knauer, Reg. No. 35,575, Brent A. Harris, Reg. No. 39,215, Jill Lynn Woodburn, Reg. No. 39,874, and Marilyn L. Amick, Reg. No. 30,444 all of Roche Diagnostics Corporation, 9115 Hague Road, P.O. Box 50457, Indianapolis, Indiana 46250, Telephone (317) 845-2000:

to prosecute and transact all business on its behalf before the United States Patent and Trademark Office in connection with any U.S. patent assigned to it and any U.S. patent application filed by it or on its behalf and to receive payments on its behalf.

Signed this 24<sup>th</sup> day of November, 1999 at Mannheim, Germany.


Roche Diagnostics GmbH

  
\_\_\_\_\_  
Signature

Dr. Bernd Kolb  
\_\_\_\_\_  
Print Name

Senior Vice President  
\_\_\_\_\_  
Position or Title

Roche Diagnostics GmbH

  
\_\_\_\_\_  
Signature

Dr. Andreas Poredda  
\_\_\_\_\_  
Print Name

Director  
\_\_\_\_\_  
Position or Title